

Technical data sheet

Kapur Hardwood decking

Product information



Weathered decking



Protected decking

Dimensions	21 x 145 x 2.75-5.9m All lengths subject to availability
Species	Kapur
Botanical name	Pryobalahops Aromatica
Origin	Southeast Asia
Description	Double Sided Grooved / Ribbed Hardwood Decking



Kapur colour	Kapur has a golden yellowish brown appearance which sometimes can include a dark red-brown with white stripes On exposure to sunlight it will fade to a silvery grey
Density	630-700-790kg / m3 at 12% humidity
Shrinkage	6% tangential 2.7% radial
Toughness	According to Janka 5500-6000N
Product applications	Suitable inside and outside in heavy constructions, bridges and water constructions in fresh water. Also suitable for screens, pergolas and park benches
Drying	The wood has a tendency for surface cracks and end cracks, especially when exposed in the sun and when it is dried quickly.
Nailing and screwing	Pre-drilling is necessary
Durability	Kapur is rated as durability Class 2 in DIN EN 350-2
Life expectancy	Up to 60 years in Use Class 3 situation (exposed out of ground contact).
Disposal of waste material	Kapur is not a hazardous substance and can be treated as a standard softwood product when disposing Any excess material can also be recycled.

Manufacturer/ Supplier

Finnforest UK Ltd, 46 Berth, Tilbury Docks, Tilbury, Essex. RM18 7HS
Tel: 01375 856855 Fax: 01375 856264 www.finnforest.co.uk

finnforest